

ABSTRACT OF THE DISCLOSURE

Reliable Cu interconnects are formed by filling an opening in a dielectric layer with Cu and then laser thermal annealing in NH_3 to reduce copper oxide and to reflow the deposited Cu, thereby eliminating voids and reducing contact resistance. Embodiments include laser thermal annealing employing an NH_3 flow rate of about 200 to about 2,000 sccm.

09986267-1000